



## Test Report: Reconstituted Wood Products Testing

**Timber Testing Centre Reference** S-29352-2022  
**Report Number** 20220331-141512  
**Testing Status** Certification  
**Samples Submitted** 18/03/2022  
**Date of Issue** 31/03/2022

**Vishnual Sajeevlal**  
**Process Engineer**  
**Borg Panels Oberon**  
**Lowes Mount Road, Oberon, NSW, 2787, Australia**

### TESTING DETAILS

**Test Method(s):**

As per method indicated in the Test Results table.  
Samples are cut in accordance with AS/NZS 4266.1.

**Test Location:**

Timber Testing Centre, Unit 2, 107 Northlink Place, Virginia, QLD, 4014

### LIMITATIONS OF REPORT

All results reported apply only to the sample tested and apply to the sample as received by the Timber Testing Centre.  
This report shall not be reproduced except in full.

## TEST RESULTS

Number of samples submitted for testing: 1

Testing Period: 18/03/2022 through 31/03/2022

<b>Sample Description *</b>		
<b>Standard</b> AS/NZS 1860.1 Particleboard Flooring	<b>Dimension</b> Pre-cut	
<b>Grade</b> Flooring - Class 1 E1	<b>Comment</b> Formaldehyde test only	
<b>Source</b> C3		
<b>Sample Number</b> 220682332		
<b>Thickness (mm)</b> 12		

Batch	Test	Method	Limit	Result (Mean)	Std Dev	Units
3-63	Panels Formaldehyde	AS/NZS 4266.1 S17	Max 1.5 mg/L	1.28	0.00	mg/L

(R) against the Batch indicates a Re-Test has been conducted.

\* Sample description information has been provided by the client

### Additions/Deviations/Exclusions:

A cutting plan is not provided. The mean and standard deviation values reported apply to the results of replicate test pieces. Panels tested for certification purposes have only had one formaldehyde test performed. The duplicate pieces shall only be tested in the case of abnormal or failed results. Moisture content testing is performed without the use of a drying desiccator. The internal desiccator temperature check for formaldehyde testing has not been recorded. Wet Bending Strength – Method C has been tested at a boiling temperature of 100oc.

## SAMPLING DETAILS

The Timber Testing Centre did not conduct sampling. Samples were submitted to the Timber Testing Centre by the client.

Regards,



**Suzie Steiger**

General Manager